

TEST REPORT

NUMBER : BKKT09000846-REV1

DATE : 22-Jan-2009

APPLICANT : **MAGICLINK GARMENT (THAILAND) CO.,LTD.**88/8 M.11 T.KLONG PRAVET, A.BAN  
PHO, CHACHENGSAO, THAILAND, 24140ATTN : **KANCHAYA (TAN) .**

SAMPLE DESCRIPTION : TWO (2) PIECES OF SUBMITTED SAMPLE SAID TO BE  
 NYLON/SPANDEX KNITTED FABRIC IN  
 A) BLACK  
 B) WHITE

STYLE NO. : ML4474,ML4474A

ORDER NO. : -

BUYER'S NAME : GALA

MANUFACTURER'S NAME : MAGICLINK GARMENT (THAILAND) CO.,LTD.

EXPORT COUNTRY : AUSTRALIA

DATE RECEIVED/DATE TEST STARTED : 20 Jan 2009

REF. : ART.#PN0193

---

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE  
 REFER TO ENCLOSED PAGE(S)

---

**CONCLUSION :**

BASED UPON THE SUBMITTED SAMPLE AND TEST RESULTS REPORTED,

	(A)	(B)
COLOUR FASTNESS TO WASHING	C	C
COLOUR FASTNESS TO RUBBING AS RECEIVED	C	NA
COLOUR FASTNESS TO PERSPIRATION	C	C

---

NOTE : M = MEETS THE PROVIDED REQUIREMENT      C = COMMERCIALLY ACCEPTABLE  
 F = BELOW THE PROVIDED REQUIREMENT      U = UNACCEPTABLE  
 \* = NO SUBMITTED INFORMATION      # = NO COMMENT  
 NA = NOT APPLICABLE

PREPARED & CHECKED BY :  
 FOR INTERTEK TESTING SERVICES LTD. [BANGKOK]



LADTAKA WONGWIBOONPORN  
 DIVISION MANAGER/TEXTILE DIVISION

TEST REPORT

NUMBER : BKKT09000846-REV1

DATE : 22-Jan-2009

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

**1. COLOUR FASTNESS TO WASHING**

ISO 105-C06:2002; TEST NO.A2S, 30 MINUTES MECHANICAL WASH AT 40°C, IN 150ML 0.4% ECE REFERENCE DETERGENT AND 0.1% SODIUM PERBORATE SOLUTION WITH 10 STEEL BALLS.

		(A)	(B)	<u>REQUIREMENT</u>
COLOUR CHANGE		4-5	4-5	3-4*
COLOUR STAINING	ACETATE	4	4-5	3-4*
	COTTON	4-5	4-5	
	NYLON	4-5	4-5	
	POLYESTER	4	4-5	
	ACRYLIC	4-5	4-5	
	WOOL	4-5	4-5	

**2. COLOUR FASTNESS TO RUBBING AS RECEIVED**

ISO 105-X12:2001

	(A) (LENGTH)	(A) (WIDTH)	(B) (LENGTH)	(B) (WIDTH)	<u>REQUIREMENT</u>
DRY	4-5	4-5	NA	NA	3-4*
WET	4-5	4-5	NA	NA	2-3*

REMARK:

NA = NOT APPLICABLE

TEST REPORT

NUMBER : BKKT09000846-REV1

DATE : 22-Jan-2009

**3. COLOUR FASTNESS TO PERSPIRATION**

ISO 105-E04:2002

ACID

		(A)	(B)	<u>REQUIREMENT</u>
COLOUR CHANGE		4-5	4-5	3-4*
COLOUR STAINING	ACETATE	4-5	4-5	3-4*
	COTTON	4-5	4-5	
	NYLON	4-5	4-5	
	POLYESTER	4-5	4-5	
	ACRYLIC	4-5	4-5	
	WOOL	4-5	4-5	

ALKALINE

		(A)	(B)	<u>REQUIREMENT</u>
COLOUR CHANGE		4-5	4-5	3-4*
COLOUR STAINING	ACETATE	4-5	4-5	3-4*
	COTTON	4-5	4-5	
	NYLON	4-5	4-5	
	POLYESTER	4-5	4-5	
	ACRYLIC	4-5	4-5	
	WOOL	4-5	4-5	

REMARK:

RATING SYSTEM:

- CLASS 5 - NO STAINING/COLOUR CHANGE
- CLASS 4 - SLIGHTLY STAINING/COLOUR CHANGE
- CLASS 3 - NOTICEABLE STAINING/COLOUR CHANGE
- CLASS 2 - CONSIDERABLE STAINING/COLOUR CHANGE
- CLASS 1 - EXCESSIVE STAINING/COLOUR CHANGE

\* THESE ARE THE GENERAL ACCEPTABLE LEVELS MOST FREQUENTLY REQUIRED BY OVERSEAS BUYERS. ATTENTION SHOULD BE DRAWN TO THE FACT THAT THE ACCEPTANCE CRITERIA MAY VARY ACCORDING TO QUALITY LEVELS OF INDIVIDUAL BUYERS AND END USE OF THE MERCHANDISE

---

## END OF THE TEST REPORT ##